ideal
Dry Mixes



STRONG BOND

Lasting Performance

Ready To Mix
Tilemate

www.idealdrymixes.com

ideal
Dry Mixes

TECHNICAL DATA SHEET – TILEMATE

PRODUCT SUMMARY	STANDARD COMPLIANCE / SPECIFICATION
Ideal Drymixes TILEMATE is a high quality polymer added, grey cement-based thin-set tile adhesive for fixing high porosity tiles like ceramic/ clay tiles, terracotta and quarry tiles of regular size. It is suitable for both vertical and horizontal surfaces, over the cementitious substrate for indoor application, in dry as well as wet areas. It also recommended for installation of Vitrified tiles on the floor.	TILEMATE complies to IS 15477:2019 - Type 1 'T' - "Specification for Adhesives for use with Ceramic Tiles and Mosaics."

TILEMATE KEY FEATURES	AREAS OF USE
➤ HIGH STRENGTH : Superior bonding strength and adhesion for long lasting tile installation performance. ➤ WATER RESISTANT : Suitable for wet areas. ➤ STRONG BOND : Good adhesive strength and bonds well with various cementitious substrates. ➤ EASY TO USE : Add water and use directly. ➤ AGE RESISTANT : Stays strong for a long time.	➤ All types of ceramic tiles, black and vitrified tiles, terracotta, some larger tiles. ➤ Cementitious screeds, plasters, concrete surfaces, bricks and other surfaces. ➤ Flooring, internal floors & some walls, dry & wet areas indoors, and residential & commercial applications.

(Consult with IDEAL experts before such applications.)

PRODUCT SPECIFICATIONS

- Colour: Grey.a
- Form: Powder.
- Mixing Ratio: 4 – 5 L water / 20 kg bag.
- Bulk Density: 1.3 – 1.5 g/cc.
- Mixing Density: 1.7 – 1.9 g/cc.
- Setting time: 24 Hours.
- Adhesive Thickness: 3 – 12 mm.
- Packaging: 20 kg and 40 kg bags.
- Coverage: 40 sqft – 55 sqft per 20 kg bag at 3 mm thickness.

(Actual coverage depends on substrate condition, trowel notch size, mortar thickness, tile size and applicator skill.)

TECHNICAL INFORMATION-APPLICATION PROPERTIES

TESTING PROPERTIES	REQUIREMENTS	TILEMATE RESULTS
Open Time (IS 15477: 2019)	Approx. 20 minutes	20 minutes
Adjustability (IS 15477: 2019)	Approx. 20 minutes	20 minutes
Pot Life	Approx. 120 minutes	120 minutes
Tensile adhesion strength:		
a. Dry condition	>= 0.5 N/mm2	>= 0.5 N/mm2
b. Wet condition	>= 0.5 N/mm2	>= 0.5 N/mm2
Sheer adhesion:		
a. Dry condition	>= 1 N/mm2	>= 1 N/mm2
b. Wet condition	>= 1 N/mm2	>= 1 N/mm2
c. Heat aging	>= 1 N/mm2	>= 1 N/mm2
Slip Resistance (T)	<= 0.5 mm	<= 0.5 mm
Application Temperature (Substrates and materials)	5oC to 35oC	5oC to 35oC

SHELF LIFE

1 year from month and year of manufacturing, for unopened bags, stored in dry condition.

SAFETY AND PRECAUTIONS

There may be irritation caused in eyes and skin in case of contact for a very long time. Please seek medical help if the problem persists for a long time. The product is recommended to be applied with gloves.

PRODUCT SPECIFICATIONS

The user should determine the usability of the product for its intended use. Our products are manufactured under the IDEAL quality standards and subjected to strict quality control procedures. Since the company has no control over site conditions and installation procedures, the company will not be responsible under any circumstances for any loss, damage, or liability from incorrect usage



ideal Dry Mixes

Ideal Drymixes (Ind) Pvt. Ltd

Reg. Off & Fac: S.F. No 247/2A, Karupur Road, Manavasi Village, Karur, Tamil Nadu - 639108

info@idealdrymixes.com
+91-8861939991,
+91-9843594429,
080-48662593